

No. 2956,

LLOYD'S REGISTER OF BRITISH AND FOREIGN SHIPPING

(Received at London Office

TESTS OF BOILER STEEL.

Date first visit _____ last visit _____ No. of visits _____

The _____ specified in the accompanying copy of Advice Notes were rolled from _____ charges. The tensile test has been applied to _____ 3 samples as set forth below, and the temper and bending tests as required by Circular No 438

No.	Purpose.	Charge Mark.	No. of plates or bars in same charge.	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Extens. in 8 ins. %	Remarks.
					Thickn.	Brdth.	Area.	Total.	Sq. Inch		
					Inch.	Inch.	Inch.	Tons.	Tons.		
1	17-10 x 33 x $\frac{7}{16}$	6760		4417	.46	1.81	.832	24.04	28.8	27.5	
2	4-8 x 9 $\frac{5}{8}$ x $\frac{5}{8}$	B557		9	.638	1.31	.835	23.5	28.1	26.	
3	8-5 x 65 $\frac{1}{2}$ x $\frac{7}{16}$	X583		7688	.44	1.56	.686	19.06	27.7	26.	

D.S.
6/10/85

D.F.
6/10/85

Fee £ : :

Expenses £ : :

£ : :

To be paid by

George Harrison
Surveyor, Lloyd's Register.

Surveyor, Lloyd's Register.

Glasgow
3-10-

3-10-86