


No. 190.

(Received in London Office)



# TESTS OF BOILER STEEL.

Tests of 31 Steel Plates manufactured by Robert Vaughan & Co of Middlesbrough  
for Boiler No. 442 to be constructed by J. Plate of Manchester  
for r

Date first visit 18<sup>th</sup> Nov last visit r No. of visits r

The 31 Plates specified in the accompanying copy of Advice Notes were rolled from  
One charge. The tensile test has been applied to 2 samples as set forth below,  
and the temper and bending tests Satisfactory

When a second test is applied, the result should be recorded immediately below the record of the original test. The number of plates or bars included in a rejection must be clearly stated.

No.	Purpose.	Charge Mark.	No. of plates or bars in same charge	Mark on plate and test piece.	Dimensions.			Ultimate Stress.		Exten. in 8 ins.	Remarks.
					Thickn.	Brdth.	Area.	Total.	Sq. Inch.		
					In.	In.	In.	Tons.	Tons.	%	
	<u>9.8 Rods 7/16 3/16</u>			<u>310</u>	<u>.44</u>	<u>1.0</u>	<u>.44</u>	<u>12.29</u>	<u>27.9</u>	<u>24.</u>	
	<u>3.5 1/2 x 9 1/2 x 3/8 "</u>			<u>316</u>	<u>.37</u>	<u>1.0</u>	<u>.37</u>	<u>10.36</u>	<u>28.0</u>	<u>25.</u>	

D.P.  
2/12/85.

Fee ..... £ : :

Expenses £ : :

£ : :

To be paid by Manufacturers

C. Kentilberg  
Surveyor, Lloyd's Register,