

For the information of Surveyors and the Committee only.

Received at

Office,

15

# Lloyd's Register of Shipping.

(Report on Machinery, No. 41433 Port *Glasgow*

*% Archibald*

No. *6398* ENGINE FORGINGS ~~OR~~ CASTINGS.

I have to report that the ~~Iron or Steel Forgings or Castings~~, as herein described, manufactured by *Wm Beadune & Co* of *Glasgow* for the Engines No. *116* being constructed by *Alex S & Co* of *Groon* for the Ship No. \_\_\_\_\_, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen. *Sound*

Forgings or Castings.

Lloyd's

No. *6398*

*A.F.*

*Alexander Fletcher*

*Glasgow 2/12/1920.*

## CRANK SHAFT.

## STRAIGHT SHAFTING.

### THRUST SHAFT.

### INTERMEDIATE SHAFTS.

### PROPELLER SHAFT.

...	<i>Superior Martin's Ingot Steel</i>		
ie ...	<i>Super</i>		
ns ...	<i>8 1/2 dia</i>	<i>8 1/2 dia</i>	
on (	<i>Forging &amp; Machining</i>		
tion (			
a Standard			
Pieces.			
Test—			
square inch	<i>30.8 30.6. 31.2.</i>	<i>30-0</i>	
on per cent	<i>32. 31. 33.</i>	<i>30</i>	
ding Test—	<i>180%</i>	<i>180%</i>	
efore fracture			
en Inspected	<i>11/10/1920 to 2/12/1920</i>		

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £

To be paid at

If iron, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.

002038-002050-0280

© 2020

*Weight. 75.*

Lloyd's Register  
Foundation

D.C.B.