

# Lloyd's Register of Shipping.

Order: 162489.

(Report on Machinery, No. 38506

Port

Shull

No. 23513

ENGINE FORGINGS ~~OR CASTINGS~~

I have to report that the Forgings ~~as~~ herein described, manufactured

by Messrs. Gutehoffnungshütte A.G.

of Sterkrade

for the Engines No. 1289 being constructed by Messrs. Charles D. Holmes & Co.

of Hull

1317

for the Ship No.

, being built by

of

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to

Hull.

on Forgings or Castings.

Lloyd's

No. 6999.

M.B. 19.7.26.

Düsseldorf 20th July 1926.

*M. Berg*

	<del>XXXXXXXXXX</del>	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	1 propeller shaft			
	<del>XXXXXXXXXX</del>			SCREW SHAFT.
Material*	Annealed Siem. Mart. Ingot Steel			
made ...	forged			
annealed ...	Yes			
Dimensions, Forgings	211 mm Ø			
Tests, Castings ...				
Pressure on inspection	rough turned			
Tests on Standard Test Pieces.	.798 3"			
Ball Test—	29,9			
Stress per square inch	32,0			
Extension per cent				
Bending Test—	180 degr. good			
Angle before fracture				
Date when Inspected	19.7.26.			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £

To be paid at Düsseldorf.

\* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.