

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_

Office, 29 APR 1930 10

# Lloyd's Register of Shipping.

(Report on Machinery, No. 41146, Port Hull)

## No. 20879 ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings or Castings, as herein described, manufactured by The Rotherham Forge & W. Mills Ltd. of Rotherham for the Engines No. 1405 being constructed by Messrs C. D. Holmes & Co. Ltd. of Hull for the Ship No. \_\_\_\_\_, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to \_\_\_\_\_

on Forgings or Castings.

R. W. Coomber

Sheffield  
16/4/30

Lloyd's  
No. as below  
R.W.C. 8/4/30


	<del>CRANK SHAFT.</del>	<del>THRUST SHAFT.</del>	<del>INTERMEDIATE SHAFT.</del>	<del>TUBE SHAFT.</del>
	/		3. <u>Con Rods</u>	1. <u>SCREW SHAFT.</u>
			<u>Premiers</u>	<u>Steel</u>
Material* ...	/		<u>Faged</u>	
Year made ...			<u>Yes</u>	
Annealed ...	/			<u>Dia 8 5/16"</u>
Dimensions, Forgings				
Weight, Castings ...	/		<u>Black</u>	<u>Forgings</u>
Progress on Inspection }			<u>454</u>	<u>R37 448.</u>
Tests on Standard Test Pieces.	/		<u>30.8</u>	<u>30.2</u>
Tensile Test—			<u>32.0</u>	<u>34.0</u>
Tons per square inch ...	/		<u>180°</u>	<u>180°</u>
Extension per cent ...			<u>180°</u>	
Cold Bending Test—	/		<u>4/4/30</u>	<u>to 8/4/30</u>
Angle before fracture ...				
Dates when Inspected	/			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £

To be paid at

\* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



© 2020

Lloyd's Register Foundation

002385-002400-0131