

9 OCT 1933

Received at

Office

10

Lloyd's Register of Shipping.

Order: 640181.

(Report on Machinery, No. 20926 Port Hamburg)

No. 33429

ENGINE FORGINGS ~~OR CASTINGS~~

The words FORGINGS or CASTINGS should be struck out as may be required.

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured by Messrs. Gutehoffnungshütte A.G. of Sterkrade for the Engines No. _____ being constructed by _____ of _____ for the Ship No. 149, being built by Messrs. Deutsche Werft of Hamburg have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Hamburg.

Mark on Forgings or Castings.

Düsseldorf 20th April 1932.

Lloyd's

No. 9605

M.B.19.4.32.

	FRANKOLSHAFIX	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	1 intern. shaft			SCREW SHAFT.
	BYWHEIK'SHIXX			
Material* ...	Annealed Siem. Mart. Ingot Steel			
How made ...	forged			
If Annealed...	Yes			
Dimensions, Forgings	450 mm Ø			
Weight, Castings				
Progress on Inspection }	rough turned			
Tests on Standard Test Pieces.	.798 3"			
Tensile Test— Tons per square inch	30,7			
Extension per cent	30,6			
Cold Bending Test— Angle before fracture	180 degr. good			
Dates when Inspected	19.4.32.			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £

To be paid at Düsseldorf.

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

