

SSEL'S NAME **s.s. "CORINTHIA".**

Report **Piræus.** No. **5320.**

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in **100^{ths}** of an inch.

STRAKE.	AMIDSHIP.						FORWARD.						AFT.						REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.					
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.				
idge																			
K SHEER STRAKE	M	58	58	54	.	4	38	37	37	1	1	42	42	42	.	.			
ke below	L	56	56	56	.	.	38	37	37	1	1	42	39	42	3	.			
K SHEER STRAKE	K	56	56	54	.	2	42	42	42	.	.	42	42	42	.	.			
Strake below	J	56	50	52	6	4	42	40	42	2	.	42	42	42	.	.			
"	H	56	48	50	8	6	42	42	42	.	.	42	42	40	.	2			
"	G	56	43	51	13	5	42	42	42	.	.	42	40	40	2	2			
"	F	56	50	50	6	6	42	40	39	2	3	42	42	39	.	3			
"	E	58	58	53	.	5	44	40	44	4	.	44	43	44	1	.			
"	D	58	56	58	2	.	44	44	39	.	5	44	39	37	5	7			
"	C	54	50	50	4	4	44	44	40	.	4	44	44	44	.	.			
"	B	54	54	54	.	.	44	44	39	.	5	44	44	44	.	.			
"	A	54	50	54	4	.	44	39	39	5	5	44	40	44	4	.			

Drillings at ends to be made in the vicinity of the peak bulkheads.

.P. Keel 90 81 9 64 60 4 64 60 4

002639-002646-0130