


9-JUL 1952

VAE P. N. Damm REPORT No.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

AMIDSHIP.					FORWARD.					AFT.					REMARKS.
Original Thickness	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		
	Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.	
•52	•52	•52			•34	•38	•36			•32	•36	•34			
•52	•52	•52			•34	•36	•36			•32	•36	•36			
•52	•54	•52			•40	•48	•48			•40	•48	•48			
•52	•56	•48		✓	•40	•58	•62			•40	•42	•42			
•52	•40	•46	12	6	•40	•62	•56			•40	•42	•40			
•52	•52	•48		✓	•40	•56	•56			•40	•42	•36		✓	
•52	•52	•48		✓	•40	4 eeder				•40	•42	•40			
•52	•46	•52	6		•40	•48	•62			•40	•46	•40			
•52	•52	•48		✓	•40	•40	•56			•40	•48	•52			
•52	•50	•44	2	8	•40	•44	•56			•40	•46	•52			



© 2021
Lloyd's Register

Drillings at ends to be made in the vicinity of the peak bulkheads.

002647-602652-0184