

For the information of Surveyors and the Committee only.

Received at

Office 30 MAY 1934

Lloyd's Register of Shipping.

(Report on Vessel No. 15130 Port *Mdb.*)

No. 1940 SHIP ~~FORGINGS OR~~ CASTINGS.

I have to report that the undermentioned ~~Iron or Steel Forgings or~~ Castings, manufactured by *MESS^{RS} HEAD WRIGHTSON & CO. L^{TD}* of *STOCKTON-ON-TEES* for the Vessel No. *237*, being built by *MESS^{RS} FURNESS S.B. CO. L^{TD}* of *STOCKTON-ON-TEES*, have been inspected by me as set forth below and found to be, so far as can be seen, **SOUND & FREE FROM DEFECT.**

Mark on Forgings or Castings.

Lloyd's
No. 1940
L.C. 28-4-34

*Jas. Grichton
Middlesbrough*

**8 DOUBLE EYES
4 STRING BACKS
8 COVER PLATES.**


	STERN FRAME.	RUDDER FRAME.	STEM.
Material* ...	ACID STEEL TROPENA CONVERTER PROCESS		
How made ...	CAST		
annealed ...	YES		
Dimensions ...	TO PATTERN		
Progress on Inspection ...	ROUGH FINISHED.		
Date when Inspected ...	26-4-34 & 28-4-34		
CASTINGS.			
Tests on Standard Test Pieces.			
Tensile Test— Tons per square inch	32.6		
Extension per cent. ...	29		
120° Bending Test— Angle before fracture	120° W.F		
Drop Test— Height from ground ...	7 feet.		
Flaming Test— If made according to Rules and found satisfactory ...	Yes		

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

(if any chargeable) £

To be paid at

If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.



The words FORGINGS or CASTINGS, IRON or STEEL, should be struck out as may be required.