

VESSEL'S NAME m.s. " INDIA ", of Copenhagen. REPORT HELSINGBORG. No. 2501.

THICKNESSES OF ~~PLATING~~ strength deck plating within half length amidship ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

FRAME.	AMIDSHIP					FORWARD					AFT					REMARKS.
	Original Thickness	Thickness by drilling.		Diminution if any.		Original Thickness	Thickness by drilling.		Diminution if any.		Original Thickness	Thickness by drilling.		Diminution if any.		
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.	
STRAKE OF STRAKE	Forward of bridge					Between hatchways										
	front (Frames					Nos. 4 & 5. (Frames										
	133-134).					50-51.										
STRAKE per STRAKE	78	77	77	1	1	78	77	77	1	1						
strake	76	75	79	1	-	67	67	65	-	2						
strake	76	71	77	5	-	67	67	67	-	-						
strake	76	67	69	9	7	64	59	59	5	5						
strake	44	43	39	1	5	44	39	43	5	1						
e-strake	44	39	-	5		44	43	-	1							

Drillings at ends to be made in the vicinity of the peak bulkheads.

002883-002890-0255