

SEL'S NAME *1/2 Diana*

Report

No.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in $\frac{1}{16}$ of an inch.

STRAKE.	AMIDSHIP.					FORWARD.					AFT.					REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.	
GE SHEER STRAKE...																
e below.....																
IR STRAKE	K	13	13	13			10	10	10			10	10	10		
ake below	J	13	13	13			10	10	8			11	11	11		
" "	H	13	13	12			11	11	11			11	11	11		
" "	G	13	11.5	11			11	11	11			11	11	10		
" "	F	13	12	13			10.5	10.5	10			10	10	10		
" "	E	13	12	13			10	9	9.5			11	11	11		
" "	O	13	13	13			12	11.5	11.5			11	11	11		
" "	C	13	Cement				13	11.5	11.5			12	12	11		
" "	B	13					14	Cement				12	12	12		
" "	A	13					15					20	Cement			
" "	KEEL	20														
" "																
" "																
" "																

Rule since 12 to 10 1/2 A.M.

© 2020

Lloyd's Register

Rule shall 12 to 10 1/2
A.M.

Drillings at ends to be made in the vicinity of the peak bulkheads.

© 2020
Lloyd's Register
Foundation

003092-003099-0187

22-7-47