

Lloyd's Register of Shipping.

Order: 33257.

(Report on Machinery, No. _____ Part _____)

DUPLICATE.

No. 26188

ENGINE FORGINGS OR CASTINGS.


I have to report that the Forgings ~~and Castings~~ as herein described, manufactured by Messrs. Klöckner-Werke A.G. Abt. Georgsmarienbergwerke of Osnabrück for the Engines No. 389 being constructed by

_____ for the Ship "Kota Baroe", being built by Messrs. My. De Schelde of Vlissingen

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Vlissingen.

Forgings or Castings.

Düsseldorf 9th January 1928.



Lloyd's
13228.
7.1.28.


1 four throw built up crank shaft

	2 crank throws		2 crank throws		2 journals		3 pins	
	Annealed		Siemens		Martin		Ingot Steel	
	forged		forged		forged		forged	
	Yes		Yes		Yes		Yes	
Forgings	520 mm Ø		520 mm Ø		520 mm Ø		520 mm Ø	
Castings	rough turned and finished		rough turned and finished		rough turned and finished		rough turned and finished	
Standard sizes.	.798 3"		.798 3"		.798 3"		.798 3"	
Weight in lb	29,5	28,7	31,1	30,4	30,1	29,7	30,4	
Percentage	35,4	29,0	30,2	34,0	32,3	33,3	31,2	
Strength Test—	180 degr. good		180 degr. good		180 degr. good		180 degr. good	
Inspected	7.1.28.		7.1.28.		7.1.28.		7.1.28.	

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(any chargeable) £

To be paid at Düsseldorf.



© 2020

Lloyd's Register Foundation

003154-003161-0035 1036

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.