

For the information of Surveyors and the Committee only.

Received at

Office

19

Lloyd's Register of Shipping.

(Report on Vessel No.

Port

Rotterdam
m.s. Kola Inden

No. 88. SHIP ~~FORGINGS OR~~ CASTINGS.

Order No. 43749.

I have to report that the undermentioned ~~Iron or Steel Forgings or~~ Castings, manufactured by *Messrs F. Schichau* of *Elbing* for the Vessel No. *306*, being built by *Messrs Maatschappij 'Fyenoord'* of *Rotterdam* have been inspected by me as set forth below and found to be, so far as can be seen, free from defects.

- One sternframe consisting of two parts. -

on ~~Forgings or~~ Castings.

Lloyd's

No. 477,478

L.C.D. J.C.D. 12.2.27

Danzig, 25th April 1927

James C. Dykes

	STERN FRAME. No. 477 UPPER PART		STERN RUBBER FRAME No 478 LOWER PART		STEM.
Material*	- annealed Siemens Martin Steel -				
How made	Cast		Cast		
Dimensions	As per plan		As per plan		
Progress on Inspection	Rough cast & finished		Rough cast & finished		
When Inspected	4 th January & 12 th February 1927		4 th January & 12 th February 1927		
CASTINGS.	245	246	247	248	
Tests on Standard Test Pieces.	*798" x 3"	*798" x 3"	*798" x 3"	*798" x 3"	
Site Test—	28.8	29.7	31.0	31.0	
Tons per square inch	32.0	30.7	32.0	32.0	
Extension per cent.	180° good	180° good	180° good	180° good	
Bending Test—	45°		8 feet		
Angle before fracture	good		good		
Height from ground ...					
Numbering Test—					
If made according to Rules and found satisfactory ...					J.C.D.

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

CNTVANGEN

8 JUNI 1927

Beantw:

Fee (if any chargeable) £ 9 : 15 : 0 (including expenses)

To be paid at by Messrs F. Schichau, Elbing.

If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.

22. T.

(A. 37)

003458-003465-0049