

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office, \_\_\_\_\_



# Lloyd's Register of Shipping.

(Report on Machinery, No. 40373 Port Hull)

No. 17448 ENGINE FORGINGS OR CASTINGS.

I have to report that the ~~Forgings or Castings~~, as herein described, manufactured by The Rotherham Forge & R. Mills Ltd. of Rotherham for the Engines No. 587/8 being constructed by Messrs Amos & Smith Ltd. of Hull for the Ship No. \_\_\_\_\_, being built by \_\_\_\_\_ of \_\_\_\_\_

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to \_\_\_\_\_

~~Forgings or Castings.~~

Lloyd's  
No. R.N.F. 9/4/29

R.W. Fawcett  
Sheffield  
17/4/29


	<del>CRANK SHAFT.</del>	<del>THRUST SHAFT.</del>	<del>INTERMEDIATE SHAFT.</del>	<del>TUBE SHAFT.</del>
	<u>2. Con. Rods.</u>			
	<del>FLYWHEEL SHAFT.</del>			<del>SCREW SHAFT.</del>
Material	<u>Siemens Steel</u>			
made	<u>Forged</u>			
aled	<u>Yes</u>			
ions, Forgings	<u>✓</u>			
Castings	<u>✓</u>			
on Standard st Pieces.	<u>664</u>			
Test— per square inch	<u>28.2</u>			
ision per cent	<u>34.0</u>			
ending Test— before fracture	<u>180°</u>			
hen Inspected	<u>6/4/29 to 9/4/29</u>			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

if any chargeable) £ ✓

To be paid at \_\_\_\_\_

If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



© 2020

Lloyd's Register  
Foundation

003541-003548-0077

003541-003548-0079