

Lloyd's Register of Shipping.

der 682

Surveyors' Office, DÜSSELDORF.

is to certify, that Malte Berg the undersigned surveyor to this society tested in
 works of Messrs. Lurub. Berg & Lütten A.G., St. Porten under Union of Dortmund
Siemens Martin Boilersteel bars specified hereunder, ordered
Messrs. Bremer Vulkan of Vegesack
 e ship No. Boiler No 630,631,632 and that the results of tests were as are set forth below.

Dimensions.			Intended for	Sample number	Charge number	Tensile tenacity			Elongation in 200 mm. in %.	Bending tests	
Length.	Breadth.	Thick-ness.				As per rules.	Ord-ered.	By test.		Cold.	Tem-pered.
3885		47 φ		1	6867	4450	47.8	21.2		good	
5000		50 φ			"	"	"	"		" "	
5000		46 φ		2	"	"	47.5	26.2		" "	
5000		43 φ			"	"	"	"		" "	

Düsseldorf, 28th February 1920.
M. Berg

This Certificate is issued upon the terms of the Rules and Regulations of the Society, which provide that:—
 While the Committee use their best endeavours to ensure that the functions of the Society are properly executed, it is to be understood
 neither the Committee nor the Society are under any circumstances whatever to be held responsible for any inaccuracy in any report
 certificate issued by the Society or its Surveyors, or in any entry in the Register Book or other publication of the Society, or for any error
 of omission, default, or negligence of the Surveyors, or other Officers or Agents of the Society."
 Material with less than 26 Tons tensile strength may not be used in the construction of boilers for classed vessels, unless specially
 sanctioned by the Committee.

1 Ton per square inch = 1,574 Kilo per square millimeter. 1 Kilo per square millimeter = 0,635 Tons per square inch.

003599-003604-0127

