

S NAME.....REPORT..... No.....

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in hundredths of an inch.

Deck

Deck

MIDSHIP. N°4															FORWARD Fr.71					AFT. Fr.50					REMARKS.
RAKE.	Original Thick-ness	Thickness by drilling.		Diminution if any.		Original Thick-ness.	Thickness by drilling.		Diminution if any.		Original Thick-ness.	Thickness by drilling.		Diminution if any.											
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.												
SHEER																									
E							.62	.49	.50	13	12		.82	.67	.63	15	19								
ake below							.56	.42	.47	14	9		.76	.63	.59	13	17								
RAKE	I.0	.92	.90	.08	.10		.56	.48	.44	12	16		.66	.55	.54	11	12								
below	.77	.67	.65	.10	.12		.56	.45	.43	11	13		.66	-	-										
"	.64	.59	.59	.05	.05		.50	.45	.43	9	11		.66	-	-										
"	.64	.59	.59	.02	.05																				
"	.64	.62	.59	.02	.05		Fr71						Fr.51												
"	.76	.70	.68	.06	.08		.82	.72	.62	10	20		.82	.65	.65	17	17								
"	.76	.71	.70	.05	.06		.76	.58	.60	18	16		.76	.62	.60	14	16								
"	.76	.74	.67	.02	.09		.66	.59	.54	7	12		.66	.55	.53	11	13								
"	.76	.60	.60	.12	.16		.66	.58	.43	8	23		.76	-	-										
"	.76	.69	.69	.07	.07		.66	.51	.48	15	18		.66	-	-										
"	I.0	.92																							
"																									
"																									

Drillings at ends to be made in the vicinity of the peak bulkheads.

004512-004519-0092