

Tests from Forgings, Made by Messrs Vickers L^{td} Sheffield
 of the National Shipyard, Chepstow

Lloyd's No	Description	Tensile Tons Per sq"	% Elongation	Bends
365	1 Intermediate Shaft	31'0	36	180°
"	"	30'8	34	"
362	1 Intermediate Shaft	31'2	34	"
"	"	29'8	34	"
440	1 Intermediate Shaft	33'0	31	"
"	"	33'0	30	"
364	1 Intermediate Shaft	32'0	29	"
"	"	31'5	31	"
439	1 Intermediate Shaft	31'5	32	"
"	"	30'2	28'5	"
338	1 Intermediate Shaft	32'8	32'5	"
"	"	33'2	31'5	"
730	1 Intermediate Shaft	30'8	30	"
"	"	32'0	32	"

W & Hume

1/5/19



© 2021

Lloyd's Register
 Foundation

006749-006759-0181