

Received at **TRIESTE** Office, 22 AUG 1927 19

## Lloyd's Register of Shipping.

Order: 12970/St

Post: 3184

Best: 10494/7401/08

(Report on Machinery, No. \_\_\_\_\_)

Port \_\_\_\_\_)

No. 2221

ENGINE FORGINGS ~~OR CASTINGS~~.

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured by **Messrs. Witkowitz Mining Steel & Iron Works** of **Witkowitz** **Corporat. Ltd.** for the Engines No. **7405** being constructed by **Messrs. Grazer Waggonfabrik AG.** of **Graz** (**Trieste**) for the Ship No. **195**, being built by **Messrs. Cantieri Navale Triestino** of **Monfalcone** for **Stabilimento Tecn. Triest.** have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to **Messrs. Grazer Waggon & Maschinenfabrik A.G. of Graz**

ck on Forgings ~~or Castings~~

V i e n n a, 18th August 1927

Lloyd's

No. 2221 65

AD. 10.8.27

1 three throw solid

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	<del>XXXXXXXXXX</del>			SCREW SHAFT.
Material * ...	S.M. Ing. Steel	/		
made ...	f o r g e d			
annealed ...	a n n e a l e d			
Dimensions, Forgings	6 11/16" Ø			
ht, Castings	- - -			
Press on } Inspection }	r o u g h t u r n e d			
on Standard Test Pieces.				
Test—				
per square inch	30.7			
	32.9			
ension per cent	80mm 32.2			
ending Test—	180 degree good			
before fracture				
When Inspected	10.8.1927			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

if any chargeable) £

To be paid at

VIENNA

© 2020

Lloyd's Register

of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

007794-007805-0206

007794-007805-0208