

Lloyd's Register of Shipping.

RESULTS OF TESTS OF STEEL.

made by Messrs. Wm Beardmore & Co. Ltd. Glasgow

The N.E. Marine Eng Co. Ltd. Wallsend-on-Tyne. Eng. No. 2797.

Batch No.	No. of Pieces.	Description.	Charge Mark.	Sample No.	Dia Thickness.	Area.	Tons per square inch.	Extension on 3 inches.	% Bend.
F. 7982/3/4/5.		Crank Pieces			1.798	.50	30.0.	32	180
" 7986		Prop. Shaft.			"	"	30.6	34	"
" 7987		Thrust Shaft			"	"	30.4	31	"
" 7988		Enter. Shaft.			"	"	30.2	27	"
" 7989		- do - do -			"	"	30.2	33	"
" 7990		- do - do -			"	"	31.2	30	"
" 7991		- do - do -			"	"	31.2	30	"
" 7992		- do - do -			"	"	30.6	29	"
" 7993		- do - do -			"	"	29.8	29	"

Chas. A. Porter.

Glasgow. 20/6/1933.

These shafts fitted in v.s. "Arcwear" N.E. Marine
No. 2797

[Signature]



© 2020

Lloyd's Register
Foundation

007993-008007-0070