



Received at _____ Office, _____ 19

Lloyd's Register of Shipping.

(Report on Machinery, No. 8077 Port Breite)

No. F.1206 ENGINE FORGINGS OR CASTINGS. Puccini

I have to report that the ~~Forgings or Castings~~, as herein described, manufactured by Messrs S.A. FIAT - I.M.T. - of Turin for the Engines No. --- being constructed by Messrs S.A. FIAT-S.G.M. - of Turin for the Ship No. "191 + 192" being built by Messrs Cantiere Navale Triestino of Monflacone have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. ~~These have been despatched to~~

Mark on Forgings ~~or Castings~~

G. Clark Vaux

Lloyd's

No. 592 ← M/S. 191

G.C.V. 11.5.28

GENOA, May 22nd, 1928

	CRANK SHAFT.	THRUST SHAFT. <u>1</u>	INTERMEDIATE SHAFT.	TUBE SHAFT.
	FLYWHEEL SHAFT.			SCREW SHAFT.
Material* ...		<u>S.M. Ingot steel</u>		
How made ...		<u>Forged</u>		
If Annealed ...		<u>Yes</u>		
Dimensions, Forgings		<u>L= 5580 m/m.</u>		
Weight, Castings ...		<u>--</u>		
Progress on Inspection }		<u>Rough forged & finished</u>		
Tests on Standard Test Pieces.		<u>592</u>		
Tensile Test—		<u>(60 x 15 m/m.)</u>		
<u>5</u> Tens per square inch		<u>48.9</u>		
<u>/m/m.</u>		<u>35</u>		
Extension per cent ...		<u>180°, good</u>		
Cold Bending Test—		<u>9, 23/3; 8 & 11/5/28. -</u>		
Angle before fracture ...				
Dates when Inspected				

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £

To be paid at

© 2020
Lloyd's Register
Foundation

If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.