

pt. 7. For the information of Surveyors and the Committee only.

Received at _____ Office, 30 JUN 1928

Lloyd's Register of Shipping.

F.1172 (Report on Machinery, No. _____ Port _____)
F.1173
F.1176

No. _____ ENGINE FORGINGS OR CASTINGS

*I have to report that the Forgings or Castings, as herein described, ~~manufactured~~
~~by~~ & finished by S.A. FIAT-Stab. Grandi Motori - of Turin
for the Engines No. 1455 being constructed by S.A. FIAT - S.G.M. -
of " Motor type M.604 A.
Turin for the Ship No. 191-193, being built by
Messrs Cantiere Navale Triestino of Monfalcone
have been inspected by me as set forth below, and found to be, so far as can
be seen, sound and free from defects. ~~These have been despatched to~~*

ck on Forgings or Castings=

Lloyd's
No. 534-535-538-538
R.M. 21.5.28

R. Jureackintosh
GENOA, June 11th 1928

	CRANK SHAFT	THRUST SHAFT	INTERMEDIATE SHAFT	TUBE SHAFT
		<u>4</u>		
	FLYWHEEL SHAFT	<u>CROSSHEADS</u>		SCREW SHAFT
Serial* ...	<u>S.M. Ingot steel</u>			
W made ...	<u>Forged</u>			
Annealed...	<u>Yes</u>			
Dimensions, Forgings	<u>To sketch</u>			
Weight, Castings ...	<u>1252 Kgs.</u>			
Progress 'on { Inspection }	<u>Rough forged & finished</u>			
Tests on Standard Test Pieces.	<u>534 - 535 - 538-538</u> <u>(60 x 15 m/m.)</u>			
Tensile Test— Tons per square inch= m/m.	<u>67.9 - 67.6 - 67.3</u>			
Extension per cent ...	<u>21.6 - 32.5 - 24.1</u>			
Old Bending Test— Angle before fracture ...	<u>180°, good</u>			
Dates when Inspected	<u>7.23/12/27 ; 7/1 ; 18 & 21/5/28 . -</u>			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fitted in motor N°1455 R. Jureackintosh

Fee (if any chargeable) £ _____ To be paid at Genoa

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.