


For the information of Surveyors and the Committee only.

Received at

Office



Lloyd's Register of Shipping.

(Report on Vessel No. 8341 Port Trieste)

M.V. Fusijama

Order No. 6551/54.

No.

SHIP FORGINGS ~~OR CASTINGS~~

I have to report that the undermentioned ~~Iron~~ Steel Forgings ~~or~~ ~~Castings~~, manufactured by Messrs. Borsig G.m.b.H. of Berlin-Tegel for the Vessel No. 773, being built by Messrs. Stabilimento Tecnico Triestino of Trieste have been inspected by me as set forth below and found to be, so far as can be seen, sound and free from surface defects.

Mark on Forgings or Castings.

Lloyd's
No. 199
W.M.18.1.29.

Bremen, 21st January, 1929.

Wilk. Meyer.

1 Tiller

~~STEEL FRAME~~

RUDDER FRAME.

STEM.

Material*	Siem. Martin Steel
How made	forged
annealed	yes
Dimensions	----
Progress on Inspection	finished
Date when Inspected	17.1.29, 18.1.29.


CASTINGS.

Tests on Standard Test Pieces.	
Tensile Test—	
Tons per square inch mm.	49.0
Extension per cent.	36.%
180° Bending Test—	
Angle before fracture	180° good
Impact Test—	
Height from ground ...	----
Numbering Test—	
If made according to Rules and found satisfactory ...	----

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any chargeable) £ : :

To be paid at Bremen.



© 2021

Lloyd's Register Foundation

If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.