

Received at

Office



# Lloyd's Register of Shipping.

(Report on Vessel No. 8341

Port Trieste

Order No. 6551/54

No.

SHIP ~~FORGINGS~~ CASTINGS.

M. V. Fusijama

The words FORGINGS or CASTINGS, IRON or STEEL, should be struck out as may be required.

We have to report that the undermentioned ~~Iron or~~ Steel ~~Forgings or~~ Castings, manufactured by Messrs. Atlas-Werke A.G. of Bremen for the Vessel No. 773, being built by Messrs. Stabilimento Tecnico of Trieste Triestino have been inspected by ~~us~~ <sup>us</sup> as set forth below and found to be, so far as can be seen, sound and free from surface defects

Mark on Forgings or Castings.

Lloyd's  
No. 197  
W.M.17.1.29.

Bremen, 21st January, 1929.

1 Quadrant half 1 Quadrant half


*Y. H. C. Kram. W. Meyer.*

	<del>SCREW FRAME</del>	<del>RUDDER FRAME</del>	STEM.
Material* ...	Siemens-Martin Steel		
How made ...	cast	cast	
Is annealed ...	yes	yes	
Dimensions ...	---	---	
Progress on Inspection ...	finished	finished	
Date when Inspected	26/9.28, 17/1.29	26/9/28, 17/1/29	
CASTINGS.			
Tests on Standard Test Pieces.	14.5 mm $\phi$ x 50 mm, 20mm $\phi$ x 200 mm.	14.5 mm $\phi$ x 50 mm, 20 mm $\phi$ x 200 mm.	
Tensile Test—			
Stress per square mm ...	46.6 43.3	48.5 44.4	
Extension per cent. ...	32 % 26 %	32 % 27.5 %	
Cold Bending Test—			
Angle before fracture	120° 120°	120° 120°	
Drop Test—			
Height from ground ...	---	---	
Hammering Test—			
If made according to Rules and found satisfactory ...	yes	yes	

SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any chargeable) £ : :

To be paid at Bremen.



© 2021

Lloyd's Register Foundation

\* If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.