

Rpt. 7.

For the information of Surveyors and the Committee only.

Received at Office, 28 JAN 1937 19

Lloyd's Register of Shipping.

(Report on Machinery, No. 9158. Port Marseille)

No. 827. ENGINE FORGINGS OR CASTINGS.

The words FORGINGS or CASTINGS should be struck out as may be required.

I have to report that the Forging ~~or Castings~~, as herein described, manufactured by Forges Paoli of Marseille for the Engine No. ~~being constructed by~~ Machinery Repairs of Steamer for the Ship No. ~~being built by~~ "Sainte Bernadette" of Tunis have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to (vessel being repaired at Marseille)

Mark on Forgings ~~or Castings~~.

Lloyd's
No. 827
W.H.W. 20.11.36

W. H. Waggott
Marseille
20.11.36


	CRANK SHAFT. M.P. valve Rod. FLYWHEEL SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT. SCREW SHAFT.
Material* ...	<u>S.M. Open hearth Steel.</u>			
How made ...	<u>Forged.</u>			
If Annealed ...	<u>Yes</u>			
Dimensions, Forgings	<u>90 to 100 mm</u>			
Weight, Castings	<u>✓</u>			
Progress on Inspection }	<u>Finished</u>			
Tests on Standard Test Pieces.				
Tensile Test—				
Tons per square inch $\frac{Kg}{cm^2}$	<u>51.9</u>			
Extension per cent	<u>34</u>			
Cold Bending Test—				
Angle before fracture	<u>180° Good.</u>			
Dates when Inspected	<u>19.11.36/20.11.36</u>			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £ Expenses

To be paid at Marse.

Lancs.
130.-
18.-



© 2021

Lloyd's Register Foundation

008641-008647-0223