

THE STEEL COMPANY OF SCOTLAND, LIMITED.

## Test Room Sheet


Newton

*Works, the*

14<sup>th</sup>

day of December

1895

ORDER NO.	QUALITY.	CHARGE NO.	SAMPLE NO.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION. <sup>in 8"</sup>			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS
				Bth.	Thk.	Area.	Actual Tons.	Per @ Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per @ Tons.	Bth.	Thk.	Area.	%	
<p>Rudder Stock for Workman Clark's No 123.</p> <p>.94 diam. .694 19.7 28.4 24.0 Bent sample to 108° without fracture 1/11/95</p>  <p>Dropped &amp; Hammered with good results 1/10/95</p> <p>Robert Whight SURVEYOR TO LLOYD'S REGISTER, GLASGOW. 14/12/95</p>																				