

THE STEEL COMPANY OF SCOTLAND, LIMITED.

Test Room Sheet


Newton

Works, the

14th

day of December

18 95

ORDER No.	QUALITY.	CHARGE No.	SAMPLE No.	SIZE OF SAMPLE.			BREAKING STRAIN.		EXTENSION.			CONDITION.		INITIAL STRAIN.		SIZE OF FRACTURE.				REMARKS		
				Bth.	Thk.	Area.	Actual Tons.	Per 8" Tons.	% Ins.	% Ins.	% Ins.	Long or Cross.	Annealed or Unannealed.	Actual Tons.	Per 8" Tons.	Bth.	Thk.	Area.	%			
4896				Rudder Frame for Workman & Clark's No. 123.																		
				.94 diam. .694 20.2 29.1 24.0. Bent sample to 103° without fracture 1/11/95																		
				 <p>Dropped & Hammered with good results 10/10/95</p> <p>Robert Munnigh</p> <p>SURVEYOR TO LLOYD'S REGISTER, GLASGOW. 14/12/95</p>																		

REL66-0021

© 2019

Lloyd's Register
Foundation

123

Steel Castings - Studer
from Fitch

18th December 1898

Hyson
Bel Rpt No. 45.16



© 2019

Lloyd's Register
Foundation