

Steel plates in Boilers No 1082

Weardale

Test No	Tms	Ea %	
1128 B	28.0	27.0	Shell plates
1123 B	28.1	26.0	
1173 E	26.0	27.0	
1128 A	27.7	25.0	
1128	27.0	24.0	
1123 A	27.6	28.0	
1123	27.6	29.0	
1123 D	28.1	27.0	
1127	28.1	26.0	Boiler ends
1127 b	28.0	26.0	
1138 B	27.0	24.0	
1138	28.4	23.0	
1138 E	27.7	25.0	
1128 b	28.7	21.0	
1133 G	27.0	28.0	
1133	26.6	28.0	
1144 D	27.4	26.0	
1144	27.0	26.0	
1144 A	26.0	28.0	
1133 A	26.7	28.0	
1127 F	29.1	26.0	Back Tube plates
1017 D	26.9	26.0 - 3 off	
1030 A	28.6	26.0	
1004	26.6	24.0	
700 K K	28.6	24.0	Flame Box Backs
700 f f	28.1	23.0	
1087 L	28.7	27.0	
1131 N	26.3	27.0	
1151	27.2	23.0	
1131 O	26.5	26.0	
1123 b	28.2	24.0	9 off Butt Straps
1093 F	26.4	26.0	6 off
1123 b	28.9	27.0	

Steel plates Boilers No. 1082 (Continued)

Test No.	Tons	Ea%.	
1001 b	28.5	27.0	14 off Roofing Stays
1001 A	27.8	24.0	17 off
988 A	27.4	23.0	2 off
1001 B	29.5	23.0	15 off
1127 G	28.9	26.0	2 off Furnace Bottoms
1033 F	27.5	30.0	4 off
1051	27.3	25.0	2 off Man Hole Rings and
1128 A	27.7	25.0	2 off
700 H H	26.8	27.0	2 off Flame Box Sides and
700 D D	28.7	27.0	2 off
700 E E	29.3	25.0	2 off
700 b b	28.6	25.0	2 off
700 I I	27.6	22.0	2 off
700 M M	26.3	24.0	
700 U U	27.3	21.0	- 2 off
700 M M	26.4	23.0	
700 F F	26.5	25.0	- 2 off
700 N N	27.2	27.0	
700 L L	26.0	23.0	
2886	26.4	25.0	Corrugated Flues
2887	26.7	28.0	
2888	26.8	23.0	
2889	26.4	24.0	
2890	26.7	23.0	
2891	27.1	23.0	

Steel Stay Bars

9929 - 109 - 2 off	1105 - 13 - 2 off	1105 - 21 - 2 off
- - - 108 - 3 off	" 4	58
- - - 106 - 2 off	" 22	
- - - 107 - 3 off	" 5 - 2 off	
- - - 62 - 2 off	" 11 - 2 off	
- - - 74 - 2 off	" 56 - 2 off	
- - - 73 - 2 off	" 14	
335 - 17 - 2 off	" 20 2 off	
" 18	" 55 - 2 off	
" 19	" 2 - 2 off	
144 - 17	" 9 - 2 off	
1105 - 6 - 2 off	" 1 - 2 off	
" 10 2 off	" 12	