

7. For the information of Surveyors and the Committee only.

Received at

Office,

Lloyd's Register of Shipping.

(Report on Machinery, No.

6987

Port

Trieste

Order No. 1560/4

No. 27

ENGINE FORGINGS OR CASTINGS

I have to report that the Iron or Steel Forgings or Castings, as herein described,

manufactured by Messrs. S. A. Armstrong of Pozzuoli

for the Engines No. - being constructed by Messrs. Stab. Tecnico Triestino,

of Trieste

for the Ship No. - being built by

of

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects

One thrust shaft, four intermediate shafts and 24 joining bolts.

According to specification: 44-50.5 chg. sq. M/M; 25-29% elong. in 50 m/m.

n Forgings or Castings.

Naples 17th September, 1925.

Lloyd's ✓ ✓ ✓ ✓

No. 70, 71, 72, 73 & 74.

1-7-25 N.G.

Nº 70 Thrust shaft - wheel shaft in 5023
Nº 71, 72, 73 & 74 in 5023

STRAIGHT SHAFTING.

~~CRANK SHAFT~~

THRUST SHAFT.

INTERMEDIATE SHAFTS.

~~PROPELLER SHAFT~~

Material ... Annealed Siemens Martin Ingot Steel

Made ... forged forged

Dimensions ... - -

Finish on { finished finished

on Standard
Test Pieces.

Test—
per square inch/m. 47.5 51.4; 47.7; 46; 47.7;

Extension per cent 30 28; 25.6; 32.6; 33.6;

Bending Test—
before fracture 180 degr. good 180 degr. good.

When Inspected 26-2-25; 2-5-25; 6-5-25; 16-5-25; 20-5-25; 31-7-25;

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Joining bolts kg. per m/m² 49.5, 47.7
elong. 32, - 33. -


Fee (if any chargeable) £

To be paid at NAPLES.

of iron, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.

† State if annealed

Assigned



© 2020

Lloyd's Register
Foundation

W1052-0074