

Extract from Certificate N°14/1-24/1 . -

Willq-0112

# Lloyd's Register of Shipping.

## RESULTS OF TESTS OF STEEL.

Made by Messrs STABILIMENTI DI DALMINE - D a l m i n e -

For Messrs Società Anonima FIAT - T u r i n -

Test.	Batch No.	Test No.	Charge Mark.	Thickness. (on machined test) pieces	Breadth.	Area.	Total, Tons.	Kgs. Tons per square inch /m/m.	Extension in 8 ins. %
6}	14/1	85	1778	6.7	28.3	189	8.9	47.0	24.5
		87	1763	6.5	28.7	187	8.7	46.5	26
		89	1763	6.5	28.7	187	8.4	44.9	30
		91	1763	6.5	28.7	187	8.7	46.5	25.5
		92	1763	6.5	28.7	187	8.6	46.0	30
		95	1741	6.9	29.2	202	8.9	44.0	28.1
		97	1741	6.9	29.2	202	9.5	46.9	26
		103	1741	6.9	29.2	202	9.3	46.0	28.1
		104	1741	6.9	29.2	202	9.5	46.9	26
		107	1741	6.5	28.7	187	9.1	48.6	25
		108	1741	6.5	28.7	187	8.6	45.9	30.4
		110	1745	6.5	28.7	187	8.6	45.9	30.4
		112	1745	6.5	28.7	187	8.6	45.9	26.5
		114	1745	6.5	28.7	187	8.5	45.5	28
		115	1745	8	30	240	11.0	46.0	25
)	24/1	131	1409	8	29.9	239	11.0	46.0	23
		134	1409	8	29.9	239	10.8	45.1	27.3
		126	1409	8	29.9	239	10.5	44	27.3

GENOA, 22nd May 1926. -

(Sgd) A.S.Mantelli

Surveyor to Lloyd's Register . -

