

will 9-0113

pt. 7.

For the information of Surveyors and the Committee only.

Received at

Office,

12

Lloyd's Register of Shipping.

(Report on Machinery, No.

Port

No. F.388 D. ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings or Castings, as herein described / ~~manufactured~~ rough forged by S.A.FIAT-I.M.T. by & finished by S.A.FIAT- Stab.Grandi Motori- of Turin for the Engines No. 1343 being constructed by S.A.FIAT - S.G.M. - of Turin for the Ship No. "VALTELLINA", being built by

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. ~~These have been dispatched to~~

R. J. Mackintosh

on Forgings or Castings.

Lloyd's

No. 55

R.M.22.5.27

GENOA, 30th January 1928

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
		1 BOSS FOR HELICAL		
	FLYWHEEL SHAFT.	WHEEL		SCREW SHAFT.
al* ...	S.M. Forged & annealed ingot steel			
made ...	Forged & annealed			
ealed ...	Yes			
sions, Forgings	To sketch			
ts, Castings ...	--			
ss on } ection }	Rough forged & finished			
on Standard st Pieces.	(55 x 20 m/m.)			
e Test— per square	46.1			
/m/m.	33.3			
ision per cent	180°, good			
ending Test— before fracture	28/9; 8/10/25 & 22/5/27 . .			
hen Inspected				

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

if any chargeable) £

To be paid at Genoa

of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.