

7. For the information of Surveyors and the Committee only.

Received at _____ Office, _____ 19

Lloyd's Register of Shipping.

F.381 F.
F.388 C.
F.462

(Report on Machinery, No. _____ Port _____)

No. F.472

ENGINE FORGINGS ~~OR CASTINGS~~

forged by Messrs

I have to report that the Forgings ~~or Castings~~, as herein described, ~~manufactured~~

S.A. FIAT-Turin & finished by FIAT - S.G.M. of Turin

for the Engines No. 1343 being constructed by S.A. FIAT - S.G.M.

of Type L.754 Turin for the Ship VALTELLINA built by

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. ~~These have been despatched to~~

Forgings ~~or Castings~~

Lloyd's

No. 34-36-51-52-70-123

R.M. 13.5.27

GENOA, 13th July, 1927 . -

R. Jackintosh

	CRANK SHAFT 4 CONNECTING RODS KEYS AND KEYSHOES	THROST SHAFT 1 COMPRESSOR CONNECTING ROD	INTERMEDIATE SHAFT 1 AIR PUMP CONNECTING ROD	TUBE SHAFT. SCREW SHAFT.
Material	S. M. Forged	and annealed ingot steel		
Condition	Forged	and annealed		
Inspected	Yes	Yes	Yes	
Sketches	To sketch	To sketch	To sketch	
Castings	--	--	--	
on { ction }	Rough forged	and finished		
on Standard t Pieces.	36 - 51 - 52 - 70 (75 x	34 20 m/m.)	123	
Test— or square inch	54.3 - 46.3 - 47.5 - 48	46.9	51	
/m/m.	33.3 - 35 - 33.3 - 35	37.5	30.8	
ion per cent				
nding Test— before fracture	180°, good	180°, good	180°, good	
en Inspected	22, 28/9; 8/10; 5, 25/11; 3/12/25	& 13/5/27 . -		

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

f any chargeable) £

To be paid at Genoa

of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.