

For the information of Surveyors and the Committee only.

Received at

Office

19

# Lloyd's Register of Shipping.

Order: 250826.

(Report on Vessel No. 16726 Port Hamburg)

No. 1075

## SHIP FORGINGS ~~OR CASTINGS~~

I have to report that the undermentioned ~~XXXXXX~~ Steel Forgings or ~~Castings~~, manufactured by Messrs. Fried. Krupp A.G. of Essen for the Vessel No. 16726, being built by Messrs. Germaniawerft of Kiel-Gaarden have been inspected by me as set forth below and found to be, so far as can be seen, 4 halves for a rudder tiller sound and free from surface defects.

on Forgings or Castings.

Lloyd's

Düsseldorf 17th January 1925.

No 171/172.

J.Q.16.1.25.

*Jul. Quack*  
Surveyor to Lloyd's Register

STEM.

171	172
2 halves for a <del>STEERNFRAME</del>	2 halves for a <del>RUDDER FRAME</del>
rudder tiller	rudder tiller
Annealed Siemens	Martin Ingot Steel

forged

forged

rough turned

rough turned

16.1.25.

16.1.25.

CASTINGS.

.798

3"

.798

3"

He Test—

32,3

31,3

ens per square inch

30,7

36,-

extension per cent.

Bending Test—

180 degr.good

180 degr.good

angle before fracture

Test—

height from ground

mering Test—

made according to Rules  
and found satisfactory ...


SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any chargeable) £

To be paid at Düsseldorf.

If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.

1. T.



© 2020

Lloyd's Register  
Foundation  
WISI - 0010 993/4