

Lloyd's Register of Shipping.

Order: 187112.

(Report on Vessel No. 16726 Port Hamburg)No. 2091
317

SHIP FORGINGS OR CASTINGS.

I have to report that the undermentioned ~~XXXXXX~~ Steel Forgings ~~XX~~
~~XXXXXX~~, manufactured by Messrs. Fried. Krupp A.G.
 of Essen for the Vessel No. 480, being built
 by Messrs. Germaniawerft of Kiel-Gaarden
 have been inspected by me as set forth below and found to be, so far as can
 be seen, 1 Stem top part and 1 Stem bottom part sound and free
from surface defects.-

on Forgings or Castings.

Lloyd's

Düsseldorf 16th February 1925.

No. 273/275.

M.B.3.2.25.

	273 1 stem XXXXXX top part Annealed Siem. Mart. Ingot Steel forged	275 1 stem XXXXXX bottom part Ingot Steel forged	STEM.
Material?			
made			
ensions			
gress on Inspection	rough turned	rough turned	
when Inspected	3.2.25.	3.2.25.	
CASTINGS.			
ats on Standard Test Pieces.	.798 3"	.798 3"	
ile Test—			
Tens per square inch	31,8	31,8	
Extension per cent.	29,3	25,2	
Bending Test—			
Angle before fracture	180 degr. good	180 degr. good	
p Test—			
Height from ground			
mering Test—			
made according to Rules and found satisfactory			


SKETCHES OF FRAMES SHOWING POSITION AND DESCRIPTION OF WELDS OF FORGINGS.

Fee (if any chargeable) £

To be paid at Düsseldorf.

If of Iron, state whether scrap or puddled Iron. If of Steel, state whether made on the Open Hearth process.

T.



© 2020

Lloyd's Register
Foundation

WISI 0013

48/49