

Lloyds Register of British & Foreign Shipping.

RESULTS OF TESTS OF STEEL.

The Tyne Iron Co. Ltd. Newcastle.
 re T & J. Horsley Ltd. London Order 9500

Test No.	Charge Mark	Thickness	Breadth	Area	Tons Area	Tons per sq. inch.	Exs in 3 ins %
31		.798 17a.		5	14.9	29.8	31
Bend 180° without fracture.							
(Signed) G. A. Hacke per. C. Marten Surveyor to Lloyds Shipping Register							



© 2020

Lloyd's Register
 Foundation

WLS48-0106