

W165-0113

A. GREEN,
SUPERINTENDENT.

Lloyd's Proving House,

Low Walker-on-Tyne, Co.

Appointed by the Committee of Lloyd's Register.

TELEPHONE No. 63827 WALLSEND.

July 27th 1940

Lloyd's Register of Shipping,
Middlesbrough.

Dear Sirs,

3/8" EMPIRE ENDURANCE.

On the 17th inst., I tested on behalf of Messrs. Smith's Dock Co. Ltd., one short length of steel link cable ex above vessel.

Both samples broke below the strain for the work size of $2\frac{3}{4}$ " 2 failures

On the 23rd, another short length was tested with the same results. 2 failures

On the 26th a further length was tested, again the samples breaking below the $2\frac{3}{8}$ " strain 2 failures

As requested a third sample was taken which passed for $2\frac{3}{8}$ " + $2\frac{1}{2}$ " respectively, but failed for $2\frac{1}{2}$ ". $2\frac{3}{8}$ $2\frac{1}{2}$

All samples failed in the iron.

Yours faithfully,
A. Green

© 2019

Lloyd's Register
Foundation



© 2019

Lloyd's Register
Foundation