

# Lloyd's Register of Shipping.

Order: A. 28960. 20/2384.

Surveyors' Office, DÜSSELDORF.

This is to certify, that Josef Lorenz the undersigned surveyor to this Society tested in the works of Kaiserliche Vereinigte Stahlwerke A.G. Hütte Röhren Heiderich of Heiderich the Siemens Martin Boiler steel Round bars specified hereunder, ordered by Thames, David, Rowan & Co. Ltd. of Glasgow for the ship No.                      Boiler No. 922 and that the results of tests were as are set forth below.

Batch-number.	Dimensions. <i>in feet inches</i>			Intended for	Sample number	Charge-number	Tensile tenacity <i>kg. p. sq. mm</i>			Elongation in 200 mm <i>%</i>	Bending tests.		Remarks.
	Length.	Breadth.	Thick-ness.				As per rules.	Ord-ered.	By test.		Cold.	Tem-pered	
8	13 <sup>1</sup> / <sub>2</sub>	1 <sup>1</sup> / <sub>2</sub>	3 <sup>1</sup> / <sub>4</sub>	Long stays	10	11789	44/55	44/51.3	45.8	28	good	good	
					9	"	"	"	45.6	26	"	"	

Düsseldorf 3<sup>rd</sup> June 1922.

J. Lorenz

Surveyor to Lloyd's Register

This Certificate is issued upon the terms of the Rules and Regulations of the Society, which provide that:

"While the Committee use their best endeavours to ensure that the functions of the Society are properly executed, it is to be understood that neither the Committee nor the Society are under any circumstances whatever to be held responsible for any inaccuracy in any report or certificate issued by the Society or its Surveyors, or in any entry in the Register Book or other publication of the Society, or for any error of judgment, default, or negligence of the Surveyors, or other Officers or Agents of the Society."

N.B.—Material with less than 26 Tons tensile strength may not be used in the construction of boilers for classed vessels, unless specially sanctioned by the Committee.

1 Ton per square inch = 1,574 Kilo per square millimeter. 1 Kilo per square millimeter = 0,635 Tons per square inch.