

Lloyd's Register of Shipping.

Order: 1637.

Surveyors' Office, DÜSSELDORF.

This is to certify, that Friedrich Kohlsaat the undersigned surveyor to this Society tested in the works of Herrn. Güterhoffnungsbrücke A. G. of Oberhausen the Siemens Martin Boiler steel Round bars specified hereunder, ordered by Herrn. David Brown & Co. Ltd. of Glasgow for the ship No. _____ Boiler No. 912 and that the results of tests were as are set forth below.

Batch-number.	Dimensions. <i>in feet & inches</i>			Intended for	Sample number	Charge-number	Tensile tenacity <i>kg. pr. sq. mm.</i>			Elongation <i>in 200 mm.</i> <i>in %.</i>	Bending tests.		Remarks.
	Length.	Breadth.	Thick-ness.				As per rules.	Ord-ered.	By test.		Cold.	Tem-pered	
13	10-0"	∅	1 3/8"	Stay bars	27	1131	41/47	41/47	45.4	24	good	good	
2	"	∅	1 1/2"	"	28	"	"	"	44.2	26	"	"	
72	"	∅	1 5/8"	"	29	9926	"	"	45.0	28	"	"	
					30	"	"	"	44.8	26	"	"	
12	"	∅	1 3/4"	"	33	"	"	"	45.9	25	"	"	
1	"	∅	2"	"	"	"	"	"	"	"	"	"	
4	"	∅	1 5/8"	"	"	"	"	"	"	"	"	"	
3	11-4 1/2"	∅	2 1/4"	Long. stays	36	206	44/55	44/50	44.4	27	"	"	
8	12-4"	∅	"	"	"	"	"	"	"	"	"	"	
12	8-6"	∅	"	"	"	"	"	"	"	"	"	"	
4	12-4"	∅	2 1/2"	"	39	"	"	"	47.3	24	"	"	

Düsseldorf 31st April 1929.
 F. Kohlsaat.
 SURVEYOR TO LLOYDS REGISTER

This Certificate is issued upon the terms of the Rules and Regulations of the Society, which provide that:—
 "While the Committee use their best endeavours to ensure that the functions of the Society are properly executed, it is to be understood that neither the Committee nor the Society are under any circumstances whatever to be held responsible for any inaccuracy in any report or certificate issued by the Society or its Surveyors, or in any entry in the Register Book or other publication of the Society, or for any error of judgment, default, or negligence of the Surveyors, or other Officers or Agents of the Society."
 N.B.—Material with less than 26 Tons tensile strength may not be used in the construction of boilers for classed vessels, unless specially sanctioned by the Committee.

1 Ton per square inch = 1,574 Kilo per square millimeter. 1 Kilo per square millimeter = 0.635 Tons per square inch.

W 481-0078

