

The Steamer "NAUSICAA" has been examined by the Society's Surveyors on the following occasions, viz.:-

DATE	PORT	REMARKS
Jan. 1923	Antwerp	When a number of plates were found pitted and the points of a large number of rivets corroded.
March, 1923	St.Nazaire	Bottom cleaned and coated and some minor damage repairs effected.
July, 1923	Rouen	Afloat. Corroded plates examined as far as practicable.
Nov. 1923	Marseilles	Special examination made of the outside plating.
June, 1924	Southampton	Special examination. Vessel had sustained damage through grounding and striking a dock entrance.
Nov. 1924	Cherbourg	Bottom cleaned and examined, found in good condition and recoated.
May, 1925	Cherbourg	Bottom cleaned and examined, found in good condition and recoated.
Jan. 1926	Chester. Pa. Philadelphia	Afloat. Heavy weather damage - 4 rivets found leaking, replaced with bolts.
Feb. 1926	Cherbourg	About 300 rivets renewed due to wear and tear. Part Special Survey No.1 carried out. 4 bolts fitted at Philadelphia replaced by rivets due to damage.



© 2019

Lloyd's Register
Foundation

W518-0229