

For the information of Surveyors and the Committee only.

Received at

Office,

19

Lloyd's Register of Shipping.

(Report on Machinery, No.

Port

No.

ENGINE FORGINGS OR CASTINGS.

I have to report that the Iron or Steel Forgings or Castings, as herein described,
manufactured by **the Rotterdam Drydock Co.** of **ROTTERDAM**,
for the Engines No. being constructed by
of
for the Ship No. **NERVIER**, being built by
of
have been inspected by me as set forth below, and found to be, so far as can
be seen, **sound and free from defects.**

rk on Forgings or Castings.

Lloyd's

No. **K.H.12965**

J.S. 21-4-27

Rotterdam, 14/5/27.

J. H. Oetman

	CRANK SHAFT.	STRAIGHT SHAFTING.		
		THRUST SHAFT.	INTERMEDIATE SHAFTS.	PROPELLER SHAFT.
Material	S.M. steel			
How made	annealed			
Dimensions	14 7/16			
Progress on Inspection				
Tests on Standard Test Pieces.				
Tensile Test—				
Tons per square inch	28 - 9			
Extension per cent	31			
Old Bending Test—				
Angle before fracture	Good.			
Dates when Inspected				

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—


Fee (if any chargeable) £

To be paid at **Rotterdam**

* If of iron, state whether scrap or puddled iron. If of steel, state whether made on the Open Hearth process.

am, 10/24. T.

† State if annealed **Yes**



© 2021

Lloyd's Register
Foundation

TUES. 19 JUL 1927