

SEL'S NAME *S.S. Scala Shell*Report *Rotterdam* No. *12231*

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in $\frac{1}{20}$ of an inch.

STRAKE.	AMIDSHIP.					FORWARD.					AFT.					REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.	
UPPER SHEER STRAKE																London letter \$ 18/4-1922 Please see Rotterdam Rep. N° 12231
Strake below																
MAIN SHEER STRAKE	13	13	13			10	10	10			10	10	10			
Strake below	12	12	12			11	11	11			9	9	9			
1st " "	13	13	13			9	9	8		1	9	9	9			
2d " "	12	12	12			11	11	10		1	9	9	9			
3d " "	13	12	12	1	1	10	10	10			10	9	10	1		
4th " "	13	13	13			12	11	12	1		10	10	10			
5th " "	13	12	13	1		10	10	9		1	10	9	9	1	1	
6th " "	13	12	12	1	1	12	12	11		1	10	9	10	1		
7th " "	13	13	12		1	10	9	10	1		10	10	10			
8th " "	13	13	12		1	11	11	10		1	10	10	9		1	
10th " "	12	11	10			8	9	9			9	8	9	1		
11th " "	12	11	11	1	1	11	10	10	1	1	9	9	9			
12th " "	12	12	12			9	9	8		1	9	9	9			
Garboard strake	13	13	13			12	12	12			12	12	12			

Drillings taken to be made in the vicinity of the peak bulkheads.