

NORTH EASTERN MARINE ENGINEERING Co., Ltd.,
NORTHUMBERLAND ENGINE WORKS,
WALLSEND-ON-TYNE.

Particulars of Results of Piston Rod. Tests
carried out on behalf of:—

Sunderland Eng. Works.

In the presence of M^r Cooper (Lloyds) Date 8/12/14
E. & B.—45430.

DESCRIPTION.	DIMENSIONS OF SAMPLE.					Contraction %	Total Load.	Tons per Sq. in.	ELONGATION.	
	Gauge Length.	Original Diam.	Original Area.	At Fracture Diam.	At Fracture Area.				Total.	%
<u>Cn 183</u>	<u>3</u>	<u>.793</u>	<u>.494</u>				<u>15.0</u>	<u>30.4</u>	<u>.72</u>	<u>24.0</u>
<u>Cn 189</u>	<u>3</u>	<u>.795</u>	<u>.496</u>				<u>14.75</u>	<u>29.7</u>	<u>.8</u>	<u>26.6</u>



© 2020

Lloyd's Register
Foundation

Works Manager.

W710-0226