

TELEGRAMS. "LLOYD'S TEST." GLASGOW
TELEPHONE, KINNING PARK 215.

LLOYD'S PROVING HOUSE,
82 ST. JAMES' STREET,
KINNING PARK,

2

Messrs Scottish Concrete Ship Co. Ltd.
Greenock


Glasgow, 20th June 1919

The following are particulars of Compression Tests applied to
Three concrete Blocks.

Number of Test	DESCRIPTION	WEIGHT lbs. ozs.	DEPTH Inches	SECTIONAL		ULTIMATE CRUSHING STRESS			MARKS
				Dimensions Inches	Area Inches	Total Tons	Per Sqr. Inch Tons	Per Sqr. Inch Pounds	
4344	1 concrete Block	5. 9½	4	4 x 4	16.0	23.05	1.44	3225	M. 3. 23/5/19
4348	1 do	5. 9½	4	4 x 4	16.0	26.8	1.64	3440	do
4349	1 do	5. 8	4	4 x 4	16.0	24.04	1.5	3360	do

By request of Messrs Scottish Concrete Ship Co. Ltd. I attach hereto
particulars supplied by them, with reference to above cubes.

E. Seedhouse
Supt.



© 2021

Lloyd's Register
Foundation

W737-0026