EL'S NAME S/Y "Panin" Report No. 834

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in 1/20 of an inch.

STRAKE.	AMIDSHIP.					FORWARD.					AFT.					REMARKS.
	Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		Original Thickness.	Thickness by drilling.		Diminution if any.		
		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.		Port.	Std.	Port.	Std.	
HEER STRAKE																The plates have been drilled in the vicinity of the peak bulkheads and amidships, and found as per margin
below.....																
SHEER STRAKE N.....	14	13+	12,5			10	10-	10-			10	10-	10-			
ake below ..... M.....	12	12-	12-			9	9-	9+			9	9	9			
" ..... L.....	12	12-	12-			11	10,5	11-			9	9-	9			
" ..... K.....	12	12-	12-			9	9	9			9	9-	9-			
" ..... J.....						11	10,5	10,5			10	10-	10-			
"																
"																
"																
"																
"																
"																

Drillings at ends to be made in the vicinity of the peak bulkheads.

W. Karl Eklund

© 2018 Lloyd's Register Foundation