

EL'S NAME Steel 4 mm Bk "PAMIR" Report Copenhagen No. 8873.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in $20^{\frac{1}{4}}$ of an inch.

STRAKE.	AMIDSHIP.				FORWARD.				AFT.				REMARKS.
	Original Thick-ness.	Thickness by drilling.		Diminution if any.	Original Thick-ness.	Thickness by drilling.		Diminution if any.	Original Thick-ness.	Thickness by drilling.		Diminution if any.	
		Port.	Std.			Port.	Std.			Port.	Std.		
DECK STRAKE													
below													
SHEER STRAKE <u>N</u>													
ake below <u>M</u>													
" <u>L</u>													
" <u>K</u>													
" <u>J</u>	13/20	13	11 1/2	1 1/2									
" <u>H</u>	13/20	14 1/2	14 1/2		10	11	11 1/2		✓10	10 1/2	11 1/2		The plates have been drilled in the vicinity of the peak bulkheads.
" <u>G</u>					12	13	12		✓10	11 1/2	12		
" <u>F</u>					10	12	11 1/2		✓10	10 1/2	12		
" <u>E</u>					11	11 1/2	11 1/2		✓9	10 1/2	11 1/2		
"													

© 2018 Andersen

Drillings at ends to be made in the vicinity of the peak bulkheads.



Lloyd's Register
Foundation