

TELEGRAMS:-  
"WEARDALE" SPENNYMOOR.

TUDHOE IRON WORKS,  
Spenny Moor

January 11<sup>th</sup> 1898.

The Weardale Iron & Coal Company Limited.  
TESTING DEPARTMENT.

Surveyor's Advice of Tests made in Weardale Siemens Steel.  
Boiler Plates & Bars ordered by Messrs. Mac Coll & Pollock.  
for their Boiler No. 20. Sunderland

Samples of Material specified in this Advice have been tested  
in my presence, and comply with Lloyd's requirements.  
Tensile 27-30 tons J.W. Sherwood.  
SURVEYOR TO LLOYD'S REGISTER.

DATE OF ORDER	No	DIMENSIONS			CAST No &c.
		LENGTH	BREADTH	THICKNESS.	
5/1/98.	18	11-0	2 1/2 Rod	18	6325 Rods 129 to 134.
	4	1 2/3	1 3/2	1/4	6416 - - 38. 39.

22 bars

J.W.S.  
SURVEYOR TO LLOYD'S REGISTER  
WEST HARTPOOL

26-1-98

