

29 APR 1930

Received at

Office

Lloyd's Register of Shipping.

(Report on Machinery, No. 41284 Port Stull)

No. 20878 ENGINE FORGINGS OR CASTINGS.

I have to report that the Forgings or Castings, as herein described, manufactured by The Rotherham Forge & R. Mills Ltd of Rotherham for the Engines No. 615 being constructed by Messrs Amos & Smith Ltd of Stull for the Ship No. _____, being built by _____ of _____

have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to _____

on Forgings or Castings.

Lloyd's

No. 2 as below
R.N.C. 8/4/30

R.W. Coomber

Sheffield
16/4/30

	CRANK SHAFT.	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	<u>3 Piston Rods</u>	<u>3 Piston Rods</u>	<u>1 Bar.</u>	<u>1 SCREW SHAFT.</u>
	<u>FLYWHEEL SHAFT.</u>			
Material	<u>Premiers</u>	<u>Forged</u>	<u>P keel</u>	
Condition		<u>Yes</u>		
Dimensions, Forgings	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<u>Dia 7 3/16"</u>	<u>Dia 8 5/16"</u>
Material, Castings	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>	<input checked="" type="checkbox"/>
Material on } specification }	<u>Black</u>		<u>Forgings</u>	
Weight on Standard Test Pieces.	<u>446</u>	<u>447</u>	<u>R38</u>	<u>R38.</u>
Weight Test— per square inch	<u>39.4</u>	<u>39.0</u>	<u>29.4</u>	<u>31.0</u>
Extension per cent	<u>24.0</u>	<u>24.0</u>	<u>33.0</u>	<u>32.0</u>
Twisting Test— before fracture	<u>180°</u>	<u>180°</u>	<u>180°</u>	<u>180°</u>
When Inspected	<u>4/4/30</u>		<u>to 8/4/30.</u>	


PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

(if any chargeable) £

To be paid at

If of wrought iron, state whether piled bars or scrap.

If of steel, state whether made by the Open Hearth process.



© 2019

Lloyd's Register
Foundation