

VESSEL'S NAME

Hellenic Prince

Report

to follow

No.

THICKNESSES OF PLATING ascertained by drilling, and comparison of same with the original thicknesses.

The thicknesses are in

decimals

of an inch.

STRAKE.	AMIDSHIP.				FORWARD.				AFT.				REMARKS.
	Original Thick-ness.	Thickness by drilling.		Diminution if any.	Original Thick-ness.	Thickness by drilling.		Diminution if any.	Original Thick-ness.	Thickness by drilling.		Diminution if any.	
		Port.	Std.			Port.	Std.			Port.	Std.		
KEEL													Original thickness of plating not stated on amidship section.
BRIDGE SHEER STRAKE	A												
Strake below	B												
SHEER STRAKE	C												
1st Strake below	D												
2nd " "	E												
3rd " "	F												
4th " "	G												
5th " "	H												
6th " "	J						46 46				52 52		
7th " "	V	60	60				46 46				42 42		
8th " "	L	60	60				46 46				42 42		
9th " "	M	70	70				45 45				42 42		
10th " "	N	45	45				42 42						
11th " "	O	35	35				32 32						
12th " "	P	50	50				32 32						

Drillings at ends to be made in the vicinity of the peak bulkheads.

002062-002070-0014

*L. Moffatt**23 Aug 1949*

© 2020

Lloyds Register
Foundation