

For the information of Surveyors and the Committee only.

Received at \_\_\_\_\_ Office, \_\_\_\_\_ 19

## Lloyd's Register of Shipping.

Order: 1611.

(Report on Machinery, No. \_\_\_\_\_ Port \_\_\_\_\_)

No. 26100. ENGINE FORGINGS OR CASTINGS

I have to report that the Forgings or Castings, as herein described, manufactured by Messrs. Th. Wuppermann of Schlebusch-Manfort for the Engines No. \_\_\_\_\_ being constructed by Messrs. Motorenfabrik Deutz A.G. of Köln-Deutz for the Ship No. 536, being built by Messrs. Abdela & Mitchell's of Queensferry, have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Köln-Deutz.

Forgings or Castings.

Lloyd's

No. 3680.

L. 31.12.27.

Düsseldorf 2nd January 1928.

J. Rogers

	THRUST SHAFT. 1 shaft	INTERMEDIATE SHAFT.	TUBE SHAFT.
	THRUST SHAFT.		SCREW SHAFT.
1* ...	Annealed Slem. Mart. Ingot Steel		
ade ...	forged		
aled ...	Yes		
ions, Forgings	155 mm Ø		
, Castings ...			
s on { ection }	rough turned		
on Standard st Pieces.	.798 3"		
Test—	53.8		
per square inch ...	28.7		
sion per cent ...	120 degr. good		
ending Test—	31.12.27.		
before fracture ...			
then Inspected			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

material has been ordered to special requirements.

if any chargeable) £

To be paid at Düsseldorf.

of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.