

957520

For the information of Surveyors and the Committee only.

Received at _____ Office, _____ 10

Lloyd's Register of Shipping.

der: 1811. (Report on Machinery, No. _____ Port _____)

No. 26102. ENGINE FORGINGS OR CASTINGS

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured by Messrs. Th. Wuppermann of Schlebusch-Manfort for the Engines No. _____ being constructed by Messrs. Motorenfabrik Deutz A.G. of Köln-Deutz for the Ship No. 535, being built by Messrs. Abdela & Mitchell's of Queensferry have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Köln-Deutz.

Forgings or Castings.

Lloyd's
No. 3882.
L. 31.12.27.

Düsseldorf 2nd January 1928.

J. Logen

	XXXXXXXXXX 1 shaft XXXXXXXXXX	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT. SCREW SHAFT.
1* ...	Annealed Siem. Mart. Ingot Steel			
ade ...	forged			
aled ...	Yes			
ons, Forgings	155 mm Ø			
Castings ...				
s on { ection }	rough turned			
on Standard t Pieces.	.798 3"			
Test— per square inch ...	33.2			
ion per cent ...	30.7			
nding Test— before fracture ...	180 degr. good			
hen Inspected	31.12.27.			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

The material has been ordered to special requirements.

if any chargeable) £

To be paid at Düsseldorf.

of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.

002101-002108-0205 451-52

Seamless, lap welded or riveted longitudinal joint lapwelded Material Mild Steel Range of tensile strength 375 Ks. mm. Work