

Lloyd's Register of Shipping.

Order: 162895. (Report on Machinery, No. _____ Port _____)

No. 26119 ENGINE FORGINGS OR CASTINGS

I have to report that the Forgings ~~or Castings~~, as herein described, manufactured by Messrs. Gutehoffnungshütte A.G. of Sterkrade for the Engines No. _____ being constructed by _____ of _____ for the Ship No. 155, being built by Messrs. Kockums mek. Verkstad of Malmö have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Malmö.

Düsseldorf 12th January 1928.

J. Hogen

Lloyd's
No. 3723/3724
J.L.11.1.28.


	XXXXXXXXXX	THRUST SHAFT.	INTERMEDIATE SHAFT.	TUBE SHAFT.
	XXXXXXXXXX			SCREW SHAFT.
Material* ...	<u>Annealed Stm. Mart. Ingot Steel</u>			
How made ...	<u>forged</u>			
Annealed...	<u>Yes</u>			
Dimensions, Forgings	<u>260 mm ø</u>			
Weight, Castings ...				
Progress on } Inspection }	<u>rough turned</u>			
Tests on Standard Test Pieces.	<u>.798</u> <u>3"</u>			
Tensile Test— Tons per square inch	<u>28,3</u> <u>28,2</u>			
Extension per cent	<u>30,6</u> <u>32,0</u>			
Cold Bending Test— Angle before fracture	<u>180 degr. good</u>			
Dates when Inspected	<u>11.1.28.</u>			

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:—

Fee (if any chargeable) £

To be paid at Düsseldorf.

* If of wrought iron, state whether piled bars or scrap. If of steel, state whether made by the Open Hearth process.



Lloyd's Register of Shipping

For the information of Surveyors and the Committee only

Order: 162825

(Report on Machinery, No. 1)

ENGINE FORGINGS

I have to report that the forgings described, manufactured by Messrs. Gutehoffnungshütte A.G. of Sterade being constructed by the engines No. 11.1.28 for the ship No. 155 being built by Messrs. Kockums Mek. Verkstedt have been inspected by me as set forth below, and found to be, so far as can be seen, sound and free from defects. These have been despatched to Malmö.

Dasseldorf 12th January 1928

[Signature]

11.1.28

No. 3728/3724

Lloyd's

Malmö

TUBE SHAFT	INTERMEDIATE SHAFT	THRUST SHAFT
XXXXXXXXXX	XXXXXXXXXX	XXXXXXXXXX
2 thrust shafts		
XXXXXXXXXX		

Annealed Stem. Mark. Ingot Steel

forged
Yes

280 mm Ø

rough turned
3"

28,2

28,0

180 deg. good

11.1.28

PARTICULARS OF OTHER TESTS APPLIED TO CASTINGS:

To be paid at Dasseldorf.

If of steel, state whether made by the Open Hearth process.



Foundation